



# PIQ-WHITE PREMIUM FILLER 70 SPECIFICATION SHEET



A JURGENSEN COMPANY

## TYPICAL PROPERTIES

Specific Gravity (Solids)	2.76	Alkalinity, Mg Na OH Eq/g	3.4
Percent Passing 325 Mesh Screen (AVE)	99%	Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ),%	.53
MIN, Passing 325 Mesh	97%	Aluminum Oxide(Al <sub>2</sub> O <sub>3</sub> ),%	.32
pH of Saturated Solution	8.6	Silicon Dioxide (SiO <sub>2</sub> ),%	1.13
Index of Refraction	1.60	Sulfur (S), %	0.09
Dry Brightness (Hunter)	80-82	Loss on Ignition, %	43.66
Oil Absorption (cc/100g.)	16-24		
Mho Hardness	3		
Bulk Density (Loose) lbs./cu. ft. (Approx.)	50.57#		
Free Moisture @ 110 Deg. C (%)	.20 max.		
Median Particle Size Range	10-13		

## TYPICAL CHEMISTRY

Total Calcium and Magnesium Carbonate	
CaCo <sub>3</sub> and Mgco <sub>3</sub>	98%
Total Insolubles	<2%

Piq-White Premium Filler 70 is fine sized dry pulverized carbonate filler. Material is available in 50 lb. paper bags, palletized and stretch wrapped, 2000 lb. mini bulk bags or in bulk. Piqua Minerals fillers are available with various average particle sizing for other filler applications.

The information and data in this bulletin are accurate to the best of our knowledge and belief, but are intended for general information only. Data referring to mechanical properties and chemical analyses are the result of tests performed on specimens obtained from specific locations of the products in accordance with prescribed sampling procedures; any warranty thereof is limited to the values obtained at such locations and by such procedures. There is no warranty with respect to values of the materials at other locations.

Piqua Materials, 1750 W. Statler Rd. Piqua, Ohio 45356

Contact: Robert Hunt, Manager of Specialty Products Telephone (800) 338-2962 Fax Number (937) 773-0791 Cell (513) 532-3022

